

(12)

(21) **2 334 615**

(22) **08.02.2001**

(51) Int. Cl. 7: **A61K 47/42, A61P 29/00,
A61P 35/00, A61P 31/04,
A61P 31/10, A61K 47/30,
A61K 31/337, A61K 31/4745**

(30) **2000-32156 JP 09.02.2000**

(71) **NANOCARRIER CO., LTD.,
5-4-6 Kashiwa-no-ha
Kashiwa-shi
277-0882, CHIBA-KEN, XX (JP).**

(72) **HONZAWA, EIICHI (JP).
YOKOYAMA, MASAYUKI (JP).
OGAWA, YASUAKI (JP).**

(74) **SMART & BIGGAR**

(54) **PROCEDE DE PRODUCTION DE MICELLE POLYMERIQUE CHARGEE DE DROGUE ET COMPOSITION DE
MICELLE POLYMERIQUE**

(54) **PRODUCTION PROCESS FOR POLYMERIC MICELLE CHARGED THEREIN WITH DRUG AND POLYMERIC
MICELLE COMPOSITION**

(57)

Provided are a production process for a polymeric micelle which is stable and has a high drug content and a composition containing such polymeric micelle. Disclosed are a production process for a polymeric micelle, comprising the steps of dissolving a drug and a specific copolymer in a water non-miscible organic solvent to prepare a solution, mixing the resulting solution with water to form an O/W type emulsion and then slowly volatilizing the organic solvent from the solution, and a polymeric micelle composition charged therein with a water-scarcely soluble drug, which can be obtained by the above production process.



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2334615 A1 2001/08/09

(21) **2 334 615**

(12) **DEMANDE DE BREVET CANADIEN
CANADIAN PATENT APPLICATION**

(13) **A1**

(22) **Date de dépôt/Filing Date:** 2001/02/08

(41) **Mise à la disp. pub./Open to Public Insp.:** 2001/08/09

(30) **Priorité/Priority:** 2000/02/09 (2000-32156) JP

(51) **Cl.Int.⁷/Int.Cl.⁷** A61K 47/42, A61K 31/4745,
A61K 31/337, A61P 29/00, A61K 47/30, A61P 31/10,
A61P 31/04, A61P 35/00

(71) **Demandeur/Applicant:**
NANOCARRIER CO., LTD., JP

(72) **Inventeurs/Inventors:**
OGAWA, YASUAKI, JP;
HONZAWA, EIICHI, JP;
YOKOYAMA, MASAYUKI, JP

(74) **Agent:** SMART & BIGGAR

(54) **Titre :** PROCEDE DE PRODUCTION DE MICELLE POLYMERIQUE CHARGEE DE DROGUE ET COMPOSITION
DE MICELLE POLYMERIQUE

(54) **Title:** PRODUCTION PROCESS FOR POLYMERIC MICELLE CHARGED THEREIN WITH DRUG AND
POLYMERIC MICELLE COMPOSITION

(57) **Abstrégé/Abstract:**

Provided are a production process for a polymeric micelle which is stable and has a high drug content and a composition containing such polymeric micelle. Disclosed are a production process for a polymeric micelle, comprising the steps of dissolving a drug and a specific copolymer in a water non-miscible organic solvent to prepare a solution, mixing the resulting solution with water to form an O/W type emulsion and then slowly volatilizing the organic solvent from the solution, and a polymeric micelle composition charged therein with a water-scarcely soluble drug, which can be obtained by the above production process.

Canada

<http://opic.gc.ca> • Ottawa-Hull K1A 0C9 • <http://cipo.gc.ca>

OPIC • CIPO 191

OPIC



CIPO

Abstract of the Disclosure

Provided are a production process for a polymeric micelle which is stable and has a high drug content and a composition containing such polymeric micelle. Disclosed are a production process for a polymeric micelle, comprising the steps of dissolving a drug and a specific copolymer in a water non-miscible organic solvent to prepare a solution, mixing the resulting solution with water to form an O/W type emulsion and then slowly volatilizing the organic solvent from the solution, and a polymeric micelle composition charged therein with a water-scarcely soluble drug, which can be obtained by the above production process.

PRODUCTION PROCESS FOR POLYMERIC MICELLE CHARGED THEREIN WITH DRUG AND POLYMERIC MICELLE COMPOSITION

Technical Field

5 The present invention relates to a production process for a polymeric micelle charged therein with a water-scarcely soluble drug and a polymeric micelle composition as a medicinal preparation.

Background Art

10 It is known to use a block copolymer having a hydrophilic segment and a hydrophobic segment for a drug carrier and how to charge a polymeric micelle formed by the above copolymer with a fixed drug (Japanese Patent Application Laid-Open No. 107565/1994 or U.S. Patent No. 5,449,513). Further, known as well are a composition containing a homogeneous polymeric micelle charged therein
15 with a water-scarcely soluble drug and a preparation method therefor (Japanese Patent Application Laid-Open No. 335267/1999).

 Described in Japanese Patent Application Laid-Open No. 107565/1994 is a method in which a micelle is charged therein with a
20 drug by forming in advance a micelle of a block copolymer in an aqueous medium, adding a drug to this micelle solution and, if necessary, mixing and stirring it under heating or supersonic treatment. Further, described in Japanese Patent Application Laid-Open No. 335267/1999 is a method for preparing a micelle therein charged with
25 a drug by dissolving a block copolymer and the drug in a water-miscible polar solvent (for example, dimethylformamide, dimethylsulfoxide and acetonitrile) and then dialyzing the solution against water.

 According to the conventional techniques described above, it can be found that various advantages are present in use of poly-
30 meric micelles as drug carriers. However, there are a case where a content of a drug charged into a polymeric micelle can not be elevated

so much depending on the kind of the drug, particularly a water-scarcely soluble drug and a case where a resulting polymeric micelle is not necessarily stable in water or a buffered aqueous solution.

5 Disclosure of the Invention

Accordingly, an object of the present invention is to provide a method in which a water-scarcely soluble (or oil-soluble) drug can readily and stably be charged into a polymeric micelle and further to provide a polymeric micelle charged therein with a stable drug
10 which can significantly raise a drug concentration in water or a buffered or isotonic aqueous solution.

The present inventors have found that a drug, particularly a water-scarcely soluble drug can efficiently be charged into a polymeric micelle by simple steps comprising dissolving a drug, particularly a water-scarcely soluble drug and a fixed block copolymer capable of forming a polymeric micelle in an aqueous medium in a water
15 non-miscible organic solvent, preparing an oil-in-water (O/W) type emulsion from the solution thus obtained and water and then volatilizing the organic solvent. Further, they have found as well that
20 suitable selection of the block copolymer used for forming a polymeric micelle makes it possible to homogeneously maintain a water-scarcely soluble drug in a very high concentration in an aqueous medium. The present invention is based on the findings described above.

Thus, according to the present invention, provided as the
25 first embodiment is:

a production process for a polymeric micelle charged is with a water-scarcely soluble drug, comprising the steps of:

- (A) dissolving a water-scarcely soluble drug and a block copolymer having a hydrophilic segment and a hydrophobic segment in a
30 water non-miscible organic solvent to prepare an organic solution,
- (B) mixing the resulting organic solution with an aqueous

medium to form an oil-in-water (O/W) type emulsion,

(C) vaporizing and removing the above organic solvent from the resulting emulsion to form a polymeric micelle solution charged therein with the above drug, and

- 5 (D) subjecting the resulting polymeric micelle solution, if necessary, to supersonic treatment and ultrafiltration treatment.

In the production process described above, a wide variety of block copolymers can be used as specifically described later.

Among them, block copolymers represented by the following Formula


- 10 (I) or (II) described in Japanese Patent Application Laid-Open No.

335267/1999 can suitably be used. It is indicated that in the method described in the above gazette, aspartate in which x to y in the following Formula (I) or (II) is 7 : 3 to 1 : 3 can not necessarily efficiently be used in charging a water-scarcely soluble drug. It has been con-


- 15 firmed, however, that according to the production process of the present invention, even such block copolymer makes it possible to efficiently charge a polymeric micelle with a drug and that the resulting polymeric micelle charged therein with the drug can stably be present in an aqueous medium.

- 20 Accordingly, provided as another embodiment of the present invention is a composition comprising a polymeric micelle originating in a block copolymer charged therein with a drug, wherein the drug is a water-scarcely soluble drug; the block copolymer is represented by the following Formula (I) or (II):

25



or



[wherein R_1 and R_3 each represent a hydrogen atom or a lower alkyl group; R_2 represents a hydrogen atom, a saturated or unsaturated C_1 to C_{29} aliphatic carbonyl group or an arylcarbonyl group; R_4 represents a hydroxyl group, a saturated or unsaturated C_1 to C_{30} aliphatic oxy group or an aryl-lower alkyloxy group; L_1 represents a linkage group selected from the group consisting of -NH-, -O- and -OCO-Z-NH- (wherein Z represents a C_1 to C_4 alkylene group); L_2 represents a linkage group selected from -OCO-Z-CO- and -NHCO-Z-CO- (wherein Z represents a C_1 to C_4 alkylene group); n represents an integer of 10 to 2500, preferably 100 to 1000; x and y may be the same or different and represent integers the total of which is 10 to 300, preferably 20 to 100; x to y falls in a range of 3 : 1 to 0 : 100, preferably 7 : 3 to 1 : 3; x and y each are present at random]; and a micelle solution prepared by dissolving or dispersing the above micelle in water can stably be maintained in a drug concentration of at least 3 mg per ml of the solution.

According to the present invention of this embodiment, a water-scarcely soluble drug which has so far been used in the form of a pharmaceutical preparation for dripping because of difficulty to prepare an aqueous liquid preparation having a high drug concentration can be used in the form of a liquid preparation having a high concentration of an effective ingredient, and it is possible as well to use the water-scarcely soluble drug in the form of an injection preparation which makes it possible to administer a required amount of an effective ingredient for short time.

Best Mode for Carrying Out the Invention


The "water-scarcely soluble drug" described in the present

invention means such a drug that is not substantially dissolved in an equivalent amount of water under an ambient environment of a room temperature and an atmospheric pressure or is distributed preferentially in a chloroform phase in a solvent system of an equivalent amount of water and chloroform. It shall not be restricted, and capable of being given as such drug are drugs including carcinostatic agents such as adriamycin, paclitaxel, docetaxel, methotrexate, vincristine, topotecan and derivatives thereof, macrolide base antibiotics such as ilotycin, erythromycin and clarisomycin, antifungal agents such as amphotericin B, itraconazole, nystatin and miconazole, steroidal antiinflammatory agents such as dexamethasone and triamcinolone, nonsteroidal antiinflammatory agents such as indomethacin and dichlofenac, hormones such as estradiol, testosterone, progesterone, diethylstilbestrol and derivatives thereof, prostaglandin, prostacyclin and other drugs for a central nervous system, drugs for a cardiovascular system and drugs for a digestive system. The method of the present invention is preferably applied to drugs having a solubility of 5 µg/ml or less in water at a room temperature. Among those described above, paclitaxel, docetaxel, camptothecin, topotecan and derivatives thereof can be given as such preferred drugs.

The "block copolymer having a hydrophilic segment and a hydrophobic segment" described in the present invention means a copolymer which can be present in an aqueous medium in the form of a core (mainly comprising hydrophobic segments)-shell (mainly comprising hydrophilic segments) type polymeric micelle and which meets the objects of the present invention. Meeting the objects of the present invention means that a polymeric micelle into which a drug is charged (introduced) can be formed at least by a method described later, and the term that a drug is charged means a state in which the drug is sealed principally in a core part (or area) of a polymeric micelle. The "hydrophilic segment" constituting such block copolymer

shall not be restricted and includes segments originating in poly-
 (ethylene oxide), poly(malic acid), poly(saccharide), poly(acrylic acid),
 poly(vinyl alcohol) and poly(vinylpyrrolidone). On the other hand, the
 "hydrophobic segment" shall not be restricted and includes segments
 5 originating in poly(β -benzyl aspartate), poly(γ -benzyl glutamate), poly-
 (β -alkyl aspartate), poly(lactide), poly(ϵ -caprolactone), poly(δ -valero-
 lactone), poly(γ -butyrolactone), poly(α -amino acid) and two or more
 kinds thereof.

Publicly known block copolymers containing such segments
 10 can be used as they are or after modified. To be specific, capable of
 being used as they are or after modified a little are those described in
 Japanese Patent Application Laid-Open No. 107565/1994 and Japa-
 nese Patent Application Laid-Open No. 335267/1999 described above,
 Japanese Patent Application Laid-Open No. 506961/ 1995 (= WO 93/
 15 16687), WO 96/33233, WO 96/32434 and WO 97/06202. In particular,
 among the block copolymers described in Japanese Patent Application
 Laid-Open No. 335267/1999, such block copolymers as specified by
 Formula (I) or (II) are particularly preferred. According to Japanese
 Patent Application Laid-Open No. 335267/1999, it is indicated that
 20 when a carboxyl group unit



in Formula (I) or (II) described above is an ester with a saturated or
 25 unsaturated C_1 to C_{30} aliphatic alcohol, particularly an ester with a
 middle or high alkyl alcohol, it is suited for charging a water-scarcely
 soluble drug into a polymeric micelle. To be unexpected, however,
 according to the present invention, in preparing, for example, mi-
 celles of paclitaxel, docetaxel, camptothecin and topotecan, the block
 30 copolymers having a form represented by Formula (I) or (II) de-
 scribed above in which an aspartate unit is partially hydrolyzed

among the block copolymers can more suitably be used in order to stabilize the polymeric micelle charged therein with the drug in an aqueous medium.

Specific examples of the respective groups shown in

- 5 Formulas (I) and (II) include the following ones. The "short chain alkyl group" represented by R_1 and R_3 can be a linear or branched chain having 1 to 6 carbon atoms and includes methyl, ethyl, isopropyl, n-butyl and isoamyl. The "saturated or unsaturated C_1 to C_{29} aliphatic carbonyl group or arylcarbonyl group" represented by R_2 can
10 be acetyl, propionyl, isopropionyl, decanoyl, dodecanoyl (lauroyl), tetradecanoyl (myristoyl), hexadecanoyl (palmitoyl), octadecanoyl, 9,12-octadecadienoyl (linoloyl), icosanoyl (arachidonoyl) and benzoyl. The "saturated or unsaturated C_1 to C_{30} aliphatic oxy group or aryl-lower alkyloxy group" represented by R_4 can be methoxy, ethoxy,
15 octyloxy, docosyloxy and benzyloxy.

- In general, L_1 and L_2 are linkage groups which can freely be changed depending on the production process of the block copolymers represented by Formulas (I) and (II). The polymer in which L_1 is -NH-, -O- or -OCO-Z-NH- can be obtained when an α -amino acid
20 chain is extended via an amino group shown below by a carbon dioxide-eliminating polymerization method (so-called NCA method) in which after forming a polyoxyethylene segment by anion-living polymerization, a hydroxyl group at a ω -terminal is converted to an amino group or a -OCO-Z-NH₂ group (Z is a C_1 to C_4 alkylene group) and
25 then an N-carboxylic acid anhydride of β -benzyl aspartate is used. Similarly, the polymer in which L_1 is -O- includes those obtained by forming a polyoxyethylene segment by anion-living polymerization and extending a polyamino acid segment at a ω -terminal thereof by the NCA method or condensing polyoxyethylene with poly- β -benzyl
30 aspartate which is separately produced by the NCA method.

The block polymer represented by Formula (II) includes

usually those which can be provided by separately producing polyoxyethylene and poly- β -benzyl aspartate and then converting a ω -terminal of polyoxyethylene to a carboxyl group or, if necessary, linking a carboxyl group with an N-terminal amino group of polyamino
5 acid via a C_1 to C_6 alkylenedicarboxylic acid.

The block copolymer containing a desired extent of the free aspartic acid unit described above can advantageously be produced by subjecting the poly- β -benzyl aspartate segment (or block) described above to a partial hydrolytic reaction. The specific production process of the block copolymer described above is specifically
10 described in Japanese Patent Application Laid-Open No. 335267/1999, and therefore it can be referred to, if necessary.

The present invention shall further be explained below with reference mainly to an example in which the block copolymer represented by Formula (I) is used, and other various block copolymers shall be able to be used as well by modifying a little.
15

The "water non-miscible organic solvent" described in the present invention means a solvent having a concept opposed to dimethylformamide, dimethylsulfoxide and acetonitrile which are
20 substantially freely miscible with water and which are used for forming a polymeric micelle in Japanese Patent Application Laid-Open No. 335267/1999. It shall not be restricted, and specific examples thereof include chloroform, methylene chloride, toluene, xylene, n-hexane or a mixture thereof.

25 In a step (A) of the process of the present invention, prepared is a solution obtained by dissolving a drug and a block copolymer in a water non-miscible organic solvent. Such solution can be prepared by separately dissolving the drug and the block copolymer in the solvents and then joining them together or mixing and
30 dissolving the drug and the block copolymer in a single vessel at the same time. If the solution containing a concentrated solute has to be

prepared, the solute is dissolved (or homogeneously dispersed) in a large amount of a solvent, and then a fixed amount of the solvent may slowly be distilled off. A preferred range of a mixing ratio of the drug used to the block copolymer can be changed depending on the kind of the drug used and a charging rate of the intended drug and therefore is not specified. In general, it is 1 : 20 to 2 : 5, preferably 1 : 10 to 1 : 3 in terms of a weight ratio of the drug to the block copolymer.

In a step (B), the organic solution thus prepared is mixed with an aqueous medium to prepare an oil-in-water (O/W) type emulsion. Water (including purified water or ion-exchanged water) or an isotonicity-reduced or buffered aqueous solution containing sodium chloride or a buffer agent can be give as an example of the aqueous medium. However, the aqueous medium may further contain a small amount of a water-miscible organic solvent and other inorganic salts (for example, sodium sulfate and the like) as long as they do not exert an adverse effect to formation of the O/W type emulsion. Usually, the organic solvent and the aqueous medium are mixed in a volume ratio of 1 : 100, preferably 1 : 20. Capable of being used for this mixing means are means conventionally used for preparing various emulsions, a mechanical stirrer, a shaker and a supersonic irradiating equipment. An operating temperature of such means shall not be restricted and is set preferably to a range of about -5 to about 40°C considering a temperature stability of the drug and a boiling point of the solvent.

Thus, the O/W type emulsion is formed, and then the mixing operation described above is continued in an open system or the organic solvent is vaporized and removed (or volatilized and removed) under reduced pressure while stirring. Thus, as volatilization of the organic solvent goes on, the emulsion is changed to a polymeric micelle solution (or dispersion).

The polymeric micelle solution may be subjected to filter-

ing treatment of insolubles and deposited matters by means of a filtering membrane as it is or after subjecting to supersonic treatment if there is a possibility that the polymeric micelle is associated or coagulated. The filtering membrane used shall not be restricted, and a membrane having a pore diameter of about 1 μm is preferred. Further, when the aqueous medium contains sodium chloride, sodium chloride contained in a physiological saline solution is removed by dialysis to obtain a micell medicine. The dialysis membrane shall not be restricted by a material and a pore diameter as long as it can efficiently separate the raw material, solvent, drug and polymer used. Usually, a cellulose membrane is used. After dialysis, supersonic treatment may further be carried out to mono-disperse the associated micelles.

The polymeric micelle according to the present invention is stable in the aqueous medium as described above, and the drug concentration in the liquid preparation can be raised. In order to elevate the drug concentration in this micelle solution (liquid preparation), concentration by filtration or freeze-drying can be carried out.

The method described above makes it possible to control the drug concentration to 10 to 30 % by weight based on the total weight of the drug and the copolymer. Further, when the copolymer represented by Formula (I) is used, capable of being provided is the composition of the aqueous medium in which the polymeric micelle can stably be maintained in a drug concentration of about 3 mg, preferably about 6 mg and particularly preferably about 10 mg per ml of the polymer micelle solution. Being capable of stably maintaining the polymeric micelle means that when the above composition is left standing at a room temperature, association between the polymeric micelles and discharge of the drug from the polymeric micelle are not brought about at least for several hours. The above association and discharge of the drug can be confirmed by optical inspection or visual

observation.

The present invention shall further be explained below with reference to specific examples, but the present shall not be restricted by these examples.

5 Examples 1 to 4: effect of a change in a proportion of the drug to the copolymer

Used was polyethylene glycol (molecular weight: 12000)-co-50 % partially hydrolyzed polybenzyl aspartate (n = 50) (hereinafter referred to as 12-50PH) (corresponding to the copolymer represented by Formula (I)). Dissolved in 5 ml of chloroform respectively
10 were 50 mg of 12-50PH and 5, 10, 15 and 20 mg of paclitaxel (obtained from Signum Ltd.), and chloroform was distilled off to adjust the amount of the chloroform solution to 0.5 ml after concentration, whereby four kinds of the chloroform solutions having different ratios
15 (in terms of a weight ratio) of the polymer to the drug were obtained (the ratios were 100 : 10, 100 : 20, 100 : 30 and 100 : 40). They were dispersed in 5 ml of a 5 % saline aqueous solution respectively and stirred vigorously for about 30 minutes to obtain four kinds of O/W emulsions. Then, chloroform was distilled off while stirring slowly at
20 a room temperature to obtain polymeric micelle solutions containing paclitaxel. They were filtered by means of a membrane having a pore diameter of 0.45 μm to remove foreign matters, and the drug contents in this stage were determined by means of HPLC. The results thereof are shown in the following Table I.

Table I

Example number	1	2	3	4
5 Drug concentration (%) in charged polymer	10	20	30	40
Entrapment (%)	69	96	71	59

10 As apparent from the results shown in Table I, it is shown
that the entrapment is high when the polymer and the drug were
charged in a ratio of 100 : 10 to 100 : 30.

Examples 5 to 6: difference in the characteristics of the polymeric
micelles according to the kind of the copolymer

15 Used were two components of 12-50PH and polyethylene
glycol (molecular weight: 12000)-co-polybenzyl aspartate (n = 25)
(hereinafter referred to as 12-25).

Used were 50 mg of the respective copolymers and 10 mg
of paclitaxel to charge the polymer with the drug in a ratio of 100 : 20
20 to prepare polymeric micelles by the same method as in Example 1
(provided that supersonic irradiation was carried out for 15 minutes
by means of a probe type supersonic apparatus before filtering by
means of a membrane having a pore diameter of 0.45 μm). The
drug-charging rates in this stage were 94 % in 12-50Ph and 64 % in
25 12-25. The concentrations of the drugs contained in the aqueous
solutions in this stage were 1.60 mg/ml and 1.23 mg/ml respectively,
and they were further filtered and concentrated. This concentration
was carried out by pressurized filtration using Mole Cut L manufac-
tured by Millipore Co., Ltd. Even if concentrated up to 10.9 mg/ml in
30 12-50PH, nothing abnormal was found in the aqueous solution, and it
was possible to further concentrate. In 12-25, however, the solution
could be concentrated only to 4.1 mg/ml, and precipitants were ad-

hered to the filtering membrane. As apparent from this result, the more concentrated paclitaxel micelle solution can be prepared in a system using partially hydrolyzed polybenzyl aspartate.

Example 7:

5 Precisely weighed into a glass-made centrifugally settling tube was 50 mg of polyethylene glycol-co-50 % partially hydrolyzed polybenzyl aspartate (12-50PH), and added thereto was 5 ml of a chloroform solution of paclitaxel having a concentration controlled to 2 mg/ml. It was stirred and dissolved, and then chloroform was
10 distilled off under nitrogen flow to adjust an amount of the chloroform solution to 0.5 ml after concentration. Added thereto was 5 ml of a 5 % sodium chloride aqueous solution, and the tube was tightly sealed and vigorously stirred to form an O/W emulsion. The tightly sealed stopper was removed 30 minutes later, and chloroform was
15 distilled off while slowly stirring at a room temperature for a whole day and night, whereby a polymeric micelle aqueous solution charged therein with the drug was obtained. The polymeric micelle solution was irradiated with a probe type supersonic apparatus for 15 minutes by applying intermittent oscillation by every second to sufficiently
20 disperse the micelles. Then, the solution was filtered by means of a filter having a pore diameter of 0.45 μm and further dialyzed to remove sodium chloride. Thereafter, a sodium chloride solution was added to reduce the solution to isotonicity. Further, the solution was pressure-filtered and concentrated by means of an Amicon ultrafilter
25 (UK200 membrane). This provided a polymeric micelle aqueous solution having a paclitaxel concentration of 13.5 mg/ml. This solution had a chloroform content of 5 ppm or less.

Example 8:

30 Precisely weighed into a glass-made centrifugally settling tube was 50 mg of polyethylene glycol-co-polybenzyl aspartate (12-25), and added thereto was 5 ml of a chloroform solution of paclitaxel

having a concentration controlled to 2 mg/ml. Hereinafter, a polymeric micelle aqueous solution containing paclitaxel was obtained in the same manner as in Example 7. The drug concentration thereof was 3.5 mg/ml.

5 Example 9:

Precisely weighed into a glass-made centrifugally settling tube was 50 mg of polyethylene glycol-co-50 % partially hydrolyzed polybenzyl aspartate (12-50PH), and added thereto was 5 ml of a chloroform solution of paclitaxel having a concentration controlled to
10 3 mg/ml. Hereinafter, a polymeric micelle aqueous solution containing paclitaxel was obtained in the same manner as in Example 7. The drug concentration thereof was 6.7 mg/ml.

Examples 10 to 13:

Used in a glass-made centrifugally settling tube respectively were four kinds of 35, 50, 65 and 75 % partially hydrolyzed
15 polybenzyl aspartates ($n = 50$) (12-50PH) of the copolymer. Each 50 mg of the respective polymers was precisely weighed, and added thereto was 5 ml of a chloroform solution of paclitaxel having a concentration controlled to 2 mg/ml to prepare four kinds of solu-
20 tions. Each was stirred and dissolved, and then chloroform was distilled off under nitrogen flow to adjust an amount of the chloroform solution to 0.5 ml after concentration. Added thereto was 5 ml of a 5 % sodium chloride aqueous solution, and the tube was tightly sealed and vigorously stirred to form an O/W emulsion. The tightly
25 sealed stopper was removed 30 minutes later, and chloroform was distilled off while slowly stirring at a room temperature for a whole day and night, whereby four kinds of polymeric micelle aqueous solutions charged therein with the drug were prepared. The polymeric micelle solutions were irradiated with a probe type supersonic
30 apparatus for 15 minutes by applying intermittent oscillation by every second to sufficiently disperse the micelles. Then, the solutions were

filtered by means of a filter having a pore diameter of 0.45 μm . The paclitaxel concentrations in a stage before concentration were 1.8, 1.9, 1.6 and 1.7 mg/ml respectively.

Example 14:

5 Precisely weighed into a glass-made centrifugally settling tube was 50 mg of polyethylene glycol (molecular weight: 5000)-co-polybenzyl aspartate ($n = 12$) (5-12), and added thereto was 5 ml of a chloroform solution of paclitaxel having a concentration controlled to 2 mg/ml. Each was stirred and dissolved, and then chloroform was
10 distilled off under nitrogen flow to adjust an amount of the chloroform solution to 0.5 ml after concentration. Added thereto was 5 ml of a 5 % sodium chloride aqueous solution, and the tube was tightly sealed and vigorously stirred to form an O/W emulsion. The tightly sealed stopper was removed 30 minutes later, and chloroform was
15 distilled off while slowly stirring at a room temperature for a whole day and night, whereby a polymeric micelle aqueous solution charged therein with the drug was prepared. The polymeric micelle solution was irradiated with a probe type supersonic apparatus for 15 minutes by applying intermittent oscillation by every second to sufficiently
20 disperse the micelles. Then, the solution was filtered by means of a filter having a pore diameter of 0.45 μm . Thereafter, a sodium chloride solution was added to reduce the solution to isotonicity. The paclitaxel concentration in a stage before concentration was 1.6 mg/ml.

25 Example 15:


Precisely weighed into a glass-made centrifugally settling tube was 50 mg of polyethylene glycol-co-polybenzyl aspartate (12-25), and added thereto was 5 ml of a chloroform solution of paclitaxel having a concentration controlled to 2 mg/ml. It was stirred and
30 dissolved, and then chloroform was distilled off under nitrogen flow to adjust an amount of the chloroform solution to 0.5 ml after concentra-

tion. Added thereto was 5 ml of a 5 % sodium chloride aqueous solution, and the tube was tightly sealed and vigorously stirred to form an O/W emulsion. The tightly sealed stopper was removed 30 minutes later, and chloroform was distilled off while slowly stirring at
5 a room temperature for a whole day and night, whereby a polymeric micelle aqueous solution charged therein with the drug was prepared. The polymeric micelle solution was irradiated with a probe type supersonic apparatus for 15 minutes by applying intermittent oscillation by every second to sufficiently disperse the micelles. Then, the
10 solution was filtered by means of a filter having a pore diameter of 0.45 μm . The paclitaxel concentration in a stage before concentration was 1.1 mg/ml.


CLAIMS

1. A production process for a polymeric micelle charged therein with a water-scarcely soluble drug, comprising the steps of:
 - (A) dissolving a water-scarcely soluble drug and a block copolymer having a hydrophilic segment and a hydrophobic segment in a water non-miscible organic solvent to prepare an organic solution,
 - (B) mixing the resulting organic solution with an aqueous medium to form an oil-in-water (O/W) type emulsion,
 - (C) vaporizing and removing the above organic solvent from the resulting emulsion to form a polymeric micelle solution charged therein with the above drug, and
 - (D) subjecting the resulting polymeric micelle solution, if necessary, to supersonic treatment and ultrafiltration treatment.
2. The production process as described in claim 1, wherein the hydrophilic segment is a segment comprising at least one selected from the group consisting of poly(ethylene oxide), poly(malic acid), poly(saccharide), poly(acrylic acid), poly(vinyl alcohol) and poly(vinylpyrrolidone).
3. The production process as described in claim 1 or 2, wherein the hydrophobic segment is a segment comprising at least one selected from the group consisting of poly(β -benzyl aspartate), poly(γ -benzyl glutamate), poly(β -alkyl aspartate), poly(lactide), poly(ϵ -caprolactone), poly(δ -valerolactone), poly(γ -butyrolactone) and poly(α -amino acid).
4. The production process as described in claim 1, wherein the hydrophilic segment comprises poly(ethylene oxide), and the hydrophobic segment is selected from the group consisting of poly(β -benzyl aspartate), poly(γ -benzyl glutamate), poly(β -benzyl aspartate-co-aspartic acid) and poly(γ -benzyl glutamate-co-glutamic acid).
5. The production process as described in claim 1, wherein the block copolymer is represented by the following Formula (I) or

(II):



or



[wherein R_1 and R_3 each represent a hydrogen atom or a lower alkyl group; R_2 represents a hydrogen atom, a saturated or unsaturated C_1 to C_{25} aliphatic carbonyl group or an arylcarbonyl group; R_4 represents a hydroxyl group, a saturated or unsaturated C_1 to C_{30} aliphatic oxy group or an aryl-lower alkyloxy group; L_1 represents a linkage group selected from the group consisting of -NH-, -O- and -OCO-Z-NH- (wherein Z represents a C_1 to C_4 alkylene group); L_2 represents a linkage group selected from -OCO-Z-CO- and -NHCO-Z-CO- (wherein Z represents a C_1 to C_4 alkylene group); n represents an integer of 10 to 2500; x and y may be the same or different and represent integers the total of which is 10 to 300; x to y falls in a range of 3 : 1 to 0 : 100; and x and y each are present at random].

6. The production process as described in claim 5, wherein x to y in Formula (I) or (II) falls in a range of 7 : 3 to 1 : 3.


7. The production process as described in any of claims 1 to 6, wherein the drug and the block copolymer are used in a weight ratio of 1 : 10 to 3 : 10.

8. The production process as described in any of claims 1 to 7, wherein the water non-miscible organic solvent is at least one selected from the group consisting of chloroform, methylene chloride, toluene, xylene and n-hexane.


9. The production process as described in any of claims 1 to 8, wherein the drug is selected from the group consisting of paclitaxel,

docetaxel and camptothecin and topotecan.

10. A composition comprising a polymeric micelle originating in a block copolymer charged therein with a drug, wherein the drug is a water-scarcely soluble drug; the block copolymer is represented by the following Formula (I) or (II):



or



[wherein R_1 and R_3 each represent a hydrogen atom or a lower alkyl group; R_2 represents a hydrogen atom, a saturated or unsaturated C_1 to C_{29} aliphatic carbonyl group or an arylcarbonyl group; R_4 represents a hydroxyl group, a saturated or unsaturated C_1 to C_{30} aliphatic oxy group or an aryl-lower alkyloxy group; L_1 represents a linkage group selected from the group consisting of -NH-, -O- and -OCO-Z-NH- (wherein Z represents a C_1 to C_4 alkylene group); L_2 represents a linkage group selected from -OCO-Z-CO- and -NHCO-Z-CO- (wherein Z represents a C_1 to C_4 alkylene group); n represents an integer of 10 to 2500; x and y may be the same or different and represent integers the total of which is 10 to 300; x to y falls in a range of 7 : 3 to 1 : 3; and x and y each are present at random]; a micelle solution prepared by dissolving or dispersing the above micelle in water can stably be maintained in a drug concentration of at least 3 mg per ml of the solution.

11. The composition as described in claim 10, wherein the drug is selected from the group consisting of paclitaxel, docetaxel, camptothecin and topotecan.

12. The composition as described in claim 10, wherein the drug

20

is paclitaxel and an analogue thereof.

Smart & Biggar
Ottawa, Canada
Patent Agents